


## Geofoam No. 5012

**Subject: Specialty Compressible Application of Geofoam**

**Date: October 2015 (Revised January 2019)**

Foam-Control® Geofoam is manufactured in conformance to ASTM D6817, “Standard Specification for Rigid Cellular Polystyrene Geofoam.” This standard covers the material properties most often required for geofoam applications. For most applications, long-term design loads should not exceed the linear elastic range of Foam-Control Geofoam which is equal to the compressive resistance at 1% deformation.

However, in some specialty compressible applications the compressive resistance at 5% and 10% deformation may be applicable. The following Table provides the compressive resistance at 5% and 10% deformation for Foam-Control Geofoam.

Foam-Control Geofoam Properties for Compressible Applications								
PRODUCT								
		12	15	19	22	29	39	46
Compressive Resistance <sup>1</sup> @ 5% deformation, min.	psi	5.1	8.0	13.1	16.7	24.7	35.0	43.5
	psf (kPa)	730 (35)	1150 (55)	1890 (90)	2400 (115)	3560 (170)	5040 (241)	6260 (300)
Compressive Resistance <sup>1</sup> @ 10% deformation, min.	psi	5.8	10.2	16.0	19.6	29.0	40.0	50.0
	psf (kPa)	840 (40)	1470 (70)	2300 (110)	2820 (135)	4180 (200)	5760 (276)	7200 (345)
ASTM D6817 Compliance, Type		EPS12	EPS15	EPS19	EPS22	EPS29	EPS39	EPS46

<sup>1</sup> See ASTM D6817 Standard for test methods and complete information.

**The compressive resistance at 5% and 10% deformation for Foam-Control Geofoam should be used only when specified by an engineer specifically for a specialty compressible application.**



Foam-Control products are manufactured by AFM Corporation licensees.

Copyright © 2019 AFM Corporation. All rights reserved. Printed in USA. Foam-Control is a registered trademark of AFM Corporation, Lakeville, MN. The Foam-Control Geofoam logo and The Trusted Lightweight Fill Material are trademarks of AFM Corporation, Lakeville, MN.