


Foam-Control® R-SHIELD® is a film-faced air barrier and weather resistive insulation used for all types of construction applications. Foam-Control R-SHIELD conforms to ASTM C578, “Standard Specification for Rigid, Cellular Polystyrene Thermal Insulation”.

Foam-Control R-SHIELD is manufactured under an industry leading quality control program monitored by UL and further recognized in UL Evaluation Report UL ER11812-01.



PRODUCT					
		100	130	150	250
Compressive Strength ^{1,2} @ 10% deformation, min. ASTM D1621	psi (kPa)	10 (69)	13 (90)	15 (104)	25 (173)
R-value ¹ , Thermal Resistance, per inch, ASTM C518	25°F ³	°F·ft ² ·h/Btu (°K·m ² /W) 4.4 (0.77)	4.5 (0.80)	4.8 (0.84)	5.0 (0.88)
	40°F ⁴	°F·ft ² ·h/Btu (°K·m ² /W) 4.2 (0.73)	4.3 (0.75)	4.6 (0.80)	4.8 (0.84)
	75°F ⁵	°F·ft ² ·h/Btu (°K·m ² /W) 3.9 (0.68)	3.9 (0.69)	4.2 (0.73)	4.4 (0.77)
Density, Nominal ASTM C303	lb/ft ³ (kg/m ³)	1.0 (16)	1.25 (20)	1.5 (24)	2.0 (32)
Flexural Strength ¹ , min. ASTM C203	psi (kPa)	25 (173)	30 (208)	35 (242)	50 (345)
Water Vapor Permeance ¹ of 1.0 in. thickness, max., perm ASTM E96		0.3	0.3	0.3	0.3
Water Absorption ¹ by total immersion, max., volume % ASTM C272		<1.0	<1.0	<1.0	<1.0
Flame Spread ASTM E84		<25	<25	<25	<25
Smoke Developed ASTM E84		<450	<450	<450	<450
ASTM C578 Compliance, Type		I	VIII	II	IX

¹ Please refer to ASTM C578 specification for complete information.

² Compressive strength is measured at 10 percent in accordance with ASTM C578. A safety factor is required to prevent long-term creep for sustained loads. For static loads, a safety factor of 3:1 is recommended.

³ Recommended for design in EXTREME COLD climates.

⁴ Recommended for design in COLD climates.

⁵ Recommended for design in WARM climates.

Thermal Performance.

The R-value of Foam-Control R-SHIELD remains constant and does not suffer from R-value loss. The closed cell structure of Foam-Control R-SHIELD contains air and not blowing agents which deplete over time.

Exposure to Water and Water Vapor.

The mechanical properties of Foam-Control R-SHIELD are unaffected by moisture. Exposure to water or water vapor does not cause swelling.

Temperature Exposure/Flame Retardants.

Foam-Control R-SHIELD is able to withstand the rigors of temperature cycling, assuring long-term performance.

Although flame retardants used in the manufacture of Foam-Control R-SHIELD provide an important margin of safety, all Foam-Control R-SHIELD products must be considered combustible.

The maximum recommended long-term exposure temperature for Foam-Control R-SHIELD is 165°F (74°C).

Weathering.

Long-term exposure to sunlight causes yellowing and a slight embrittlement of the surface due to ultraviolet light. This has little effect on mechanical properties. If stored outdoors, cover Foam-Control R-SHIELD with opaque polyethylene film, tarps, or similar material.

Termite Resistant - Perform Guard®.

Foam plastic insulations have been shown to become termite infested under certain exposure conditions. Foam-Control R-SHIELD with Perform Guard® provides resistance to termite infestation. Please review literature on Foam-Control R-SHIELD with Perform Guard for complete information.

Resistance to Mold and Mildew.

Foam-Control R-SHIELD will not decompose and will not support mold or mildew growth. Foam-Control R-SHIELD provides no nutrient value to plants or animals.

Adhesives, Coatings, and Chemicals.

Solvents which attack Foam-Control R-SHIELD include esters, ketones, ethers, aromatic, and aliphatic hydrocarbons and their emulsions, among others. If Foam-Control R-SHIELD is to be placed in contact with materials (or their vapors) of unknown composition, pretest for compatibility at maximum exposure temperature.

Do not install or use Foam-Control R-SHIELD with coal tar pitch, highly solvent-extended mastics, or solvent-based adhesives without adequate separation.

Warranty.

Foam-Control R-SHIELD Licensees offer a product warranty ensuring thermal performance, physical properties, and termite resistance.

ACH

FOAM TECHNOLOGIES

WWW.ACHFOAM.COM



Foam-Control products are manufactured by AFM Corporation licensees.

Copyright © 2019 AFM Corporation. All rights reserved. Printed in USA. Foam-Control, Perform Guard, and R-SHIELD are registered trademarks of AFM Corporation, Lakeville, MN. The Foam-Control R-Shield logo is a trademark of AFM Corporation, Lakeville, MN.

UL logo is a registered trademark of UL LLC. USGBC logo is a registered trademark of U.S. Green Building Council.

RS02-01/19



www.foam-control.com

**AIR BARRIER &
WEATHER RESISTIVE
INSULATION**